

		ALDI RSL Limits		
Substance	CAS-no.	Product section / Limits - Textiles <sup>1)</sup>	Product section / Limits - Shoes <sup>1)</sup>	Test Method <sup>9)</sup>
<b>1. Alkylphenols / Alkylphenoethoxylates (AP/APEO)</b>				
Octylphenol OP	Various	OP, NP: 5 mg/kg (sum) OP(EO), NP(EO): 50 mg/kg (sum)	OP, NP: 50 mg/kg (sum) OP(EO), NP(EO): 50 mg/kg (sum)	DIN EN ISO 18254-1 (Textile) / DIN EN ISO 21084 (Textile) DIN EN ISO 18218-1 (Leather) Solvent extraction: Methanol GC-MS / LC-MS (AP + APEO <sub>(1-2)</sub> ) & LC-MS (APEO <sub>(3-18)</sub> )
4-(1,1,3,3-Tetramethylbutyl)-phenol	140-66-9			
Octylphenol	27193-28-8			
4-Octylphenol	1806-26-4			
Nonylphenol NP	various			
4-Nonylphenol	104-40-5			
Nonylphenol	25154-52-3			
Nonylphenol (branched)	90481-04-2			
4-Nonylphenol (branched)	84852-15-3			
Nonylphenol Ethoxylates NPEO <sub>(1-2)</sub>	various			
Nonylphenol Ethoxylates NPEO <sub>(3-18)</sub>	various			
(Nonylphenoxy)-polyethylenoxid	9016-45-9			
4-Nonylphenol, ethoxylated	26027-38-3			
Poly(oxy-1,2-ethanediyl), .alpha.- (nonylphenyl)-.omega.-hydroxy-, branched	68412-54-4			
4-Nonylphenol, branched, ethoxylated	127087-87-0			
Unbekanntes Farbmittel 94 (SIN list Isononylphenol-ethoxylate)	37205-87-1			
Octylphenol Ethoxylates OPEO <sub>(1-2)</sub>	various			
Octylphenol Ethoxylates OPEO <sub>(3-18)</sub>	various			
alpha-[4-(1,1,3,3- Tetramethylbutyl)phenyl]-w- hydroxypoly(oxy-1,2-ethandiyl) (SIN List OPEs)	9002-93-1			
4-tert-Octylphenoethoxylate	9036-19-5			
4-tert-Octylphenoethoxylate (branched)	68987-90-6			

		ALDI RSL Limits		
Substance	CAS-no.	Product section / Limits - Textiles <sup>1)</sup>	Product section / Limits - Shoes <sup>1)</sup>	Test Method <sup>9)</sup>
<b>2. Phthalates</b>				
Di-Butyl Phthalate (DBP)	84-74-2	250 mg/kg (sum)	500 mg/kg (sum)	DIN EN ISO 14389 or CPSC-CH-C1001-09.3 Solvent extraction: THF GC-MS analysis
Di(2-Ethyl Hexyl) Phthalate (DEHP)	117-81-7			
Benzyl Butyl Phthalate (BBP)	85-68-7			
Di-Iso-Nonyl Phthalate (DINP)	28553-12-0, 68515-48-0			
Di-N-Octyl Phthalate (DNOP)	117-84-0			
Di-Iso-Decyl Phthalate (DIDP)	26761-40-0, 68515-49-1			
Di-Iso-Butyl Phthalate (DIBP)	84-69-5			
Di-N-Hexyl Phthalate (DNHP)	84-75-3			
Di-(2-methoxyethyl) Phthalate (DMEP)	117-82-8			
DHNUP	68515-42-4			
DIHP	71888-89-6			
DPP	131-18-0			
Diisopentylphthalate (DIPP)	605-50-5			

		ALDI RSL Limits		
Substance	CAS-no.	Product section / Limits - Textiles <sup>1)</sup>	Product section / Limits - Shoes <sup>1)</sup>	Test Method <sup>9)</sup>
<b>3. Brominated and Chlorinated Flame Retardants<sup>3)</sup></b>				
Polybrominated biphenyls (PBBs)	59536-65-1 various	10 mg/kg (each)	10 mg/kg (each)	DIN EN ISO 17881-1 and DIN EN ISO 17881-2 Solvent extraction: Toluol / Acetone / THF GC-MS / LC-MS analysis
Monobromo biphenyls (MonoBB)				
Dibromo biphenyls (DiBB)	-			
Tribromo biphenyls (TriBB)	-			
Tetrabromo biphenyls (TetraBB)	-			
Pentabromo biphenyls (PentaBB)	-			
Hexabromo biphenyls (HexaBB)	-			
Heptabromo biphenyls (HeptaBB)	-			
Octabromo biphenyls (OctaBB)	-			
Nonabromo biphenyls (NonaBB)	-			
Decabromo biphenyl (DecaBB)	13654-09-6			
Polybrominated diphenyl ethers (PBDEs)	various			
Monobromo diphenyl ethers (MonoBDE)	-			
Dibromo diphenyl ethers (DiBDE)	-			
Tribromo diphenyl ethers (TriBDE)	-			
Tetrabromo diphenyl ethers (TetraBDE)	40088-47-9			
Pentabromo diphenyl ethers (PentaBDE)	32534-81-9			
Hexabromo diphenyl ethers (HexaBDE)	36483-60-0			
Heptabromo diphenyl ethers (HeptaBDE)	68928-80-3			
Octabromo diphenyl ethers (OctaBDE)	32536-52-0			
Nonabromo diphenyl ethers (NonaBDE)	63936-56-1			
Decabromo diphenyl ether (DecaBDE)	1163-19-5			
Tris(2,3-Dibromopropyl)-Phosphate	126-72-7			
Tris(2-Chloroethyl)Phosphate (TCEP)	115-96-8			
Hexabromocyclododecane (HBCDD)	134237-50-6, 134237-51-7, 134237-52-8, 25637-99-4, 3194-55-6			
Tetrabromo-bisphenol A (TBBPA)	79-94-7			

		ALDI RSL Limits		
Substance	CAS-no.	Product section / Limits - Textiles <sup>1)</sup>	Product section / Limits - Shoes <sup>1)</sup>	Test Method <sup>9)</sup>
<b>Subgroup: Other Flame Retardants</b>				
TEPA	545-55-1	best current technology	best current technology	DIN EN ISO 17881-2 Solvent extraction: Toluol / Acetone / THF GC-MS / HPLC-MS analysis  For boron and antimony (total): Microwave extraction with nitric acid/hydrochloric acid ICP-MS analysis
TRIS	126-72-7			
Sodium tetraborate	1303-96-4 1303-43 4 12179-04-3 215- 540-4			
Boron trioxide	1303-86-2			
Boric acid	10043-35-3 11113- 50-1			
Antimony trioxide	1309-64-4			
Tri-o-cresyl phosphate	78-30-8			
Tris(1,3-dichloro-2-propyl)phosphate (TDCPP)	13674-87-8			
<b>4. Amines (associated with Azo dyes/ colorants)</b>				
4-Aminodiphenyl	92-67-1	< 20 mg/kg (each)	< 20 mg/kg (each)	DIN EN ISO 14362-1 and DIN EN ISO 14362- 3 (Textile) DIN EN ISO 17234-1 and DIN EN ISO 17234- 2 (Leather)
Benzidine	92-87-5			
4-Chloro-o-Toluidine	95-69-2			
2-Naphthylamine	91-59-8			
o-Aminoazotoluene	97-56-3			
2-Amino-4-Nitrotoluene	99-55-8			
p-Chloroaniline	106-47-8			
2,4-Diaminoanisole	615-05-4			
4,4'-Diaminodiphenylmethane	101-77-9			
3,3'-Dichlorobenzidine	91-94-1			
3,3'-Dimethoxybenzidine	119-90-4			
3,3'-Dimethylbenzidine	119-93-7			
3,3'-Dimethyl- 4,4'-diaminodiphenylmethane	838-88-0			
p-Cresidine	120-71-8			
4,4'-Methylene-Bis(2-Chloroaniline)	101-14-4			
4,4'-Oxydianiline	101-80-4			
4,4'-Thiodianiline	139-65-1			
o-Toluidine	95-53-4			
2,4-Toluylenediamine	95-80-7			
2,4,5-Trimethylaniline	137-17-7			
o-Anisidine	90-04-0			
p-Aminoazobenzene	60-09-3			
2,4-Xylidine	95-68-1			
2,6-Xylidine	87-62-7			

		ALDI RSL Limits		
Substance	CAS-no.	Product section / Limits - Textiles <sup>1)</sup>	Product section / Limits - Shoes <sup>1)</sup>	Test Method <sup>9)</sup>
<b>Subgroup: Carcinogenic dyes</b>				
C.I Acid Red 26	3761-53-3	< 20 mg/kg (each)	< 20 mg/kg (each)	DIN 54231 Solvent extraction: Methanol (Solvent extraction: Pyridine according to DIN 16373-2 for special cases) HPLC-DAD-MS
C.I. Basic Red 9	569-61-9			
C.I. Basic Violet 3 (with ≥ 0,1 % Michler's ketone or base)	548-62-9			
C.I. Basic Violet 14	632-99-5			
C.I Direct Blue 6	2602-46-2			
C.I Direct Red 28	573-58-0			
C.I Direct Black 38	1937-37-7			
C.I Disperse Blue 1	2475-45-8			
C.I. Disperse Yellow 3	2832-40-8			
C.I. Disperse Orange 11	82-28-0			
C.I. Disperse Yellow 23	6250-23-3			
C.I. Disperse Orange 149	85136-74-9			
C.I. Solvent Yellow 1	60-09-3			
C.I. Solvent Yellow 2	60-11-7 EN71-9			
C.I. Solvent Yellow 3	97-56-3			
C.I. Solvent Yellow 14	842-07-9			
C.I. Basic Blue 26	2580-56-5			
C.I. Basic Violet 1	8004-87-3 EN71-9			
C.I. Direct Brown 95	16071-86-6			
C.I. Direct Blue 15	2429-74-5			
C.I. Direct Blue 218	28407-37-6			
C.I Acid Red 114	6459-94-5			
C.I Acid Violet 49	1694-09-3			

		ALDI RSL Limits		
Substance	CAS-no.	Product section / Limits - Textiles <sup>1)</sup>	Product section / Limits - Shoes <sup>1)</sup>	Test Method <sup>9)</sup>
<b>Subgroup: Allergenic Disperse Dyes</b>				
C.I. Disperse Blue 1	2475-45-8	< 20 mg/kg (each)	< 20 mg/kg (each)	DIN 54231 Solvent extraction: Methanol (Solvent extraction: Pyridine according to DIN 16373-2 for special cases) HPLC-DAD-MS
C.I. Disperse Blue 3	2475-46-9			
C.I. Disperse Blue 7	3179-90-6			
C.I. Disperse Blue 26	3860-63-7			
C.I. Disperse Blue 35	12222-75-2			
C.I. Disperse Blue 102	12222-97-8			
C.I. Disperse Blue 106	12223-01-7			
C.I. Disperse Blue 124	61951-51-7			
C.I. Disperse Brown 1	23355-64-8			
C.I. Disperse Orange 1	2581-69-3			
C.I. Disperse Orange 3	730-40-5			
C.I. Disperse Orange 37/76	13301-61-6			
C.I. Disperse Red 1	2872-52-8			
C.I. Disperse Red 11	2872-48-2			
C.I. Disperse Red 17	3179-89-3			
C.I. Disperse Yellow 1	119-15-3			
C.I. Disperse Yellow 3	2832-40-8			
C.I. Disperse Yellow 9	6373-73-5			
C.I. Disperse Yellow 39	12236-29-2			
C.I. Disperse Yellow 49	54824-37-2			

		ALDI RSL Limits		
Substance	CAS-no.	Product section / Limits - Textiles <sup>1)</sup>	Product section / Limits - Shoes <sup>1)</sup>	Test Method <sup>9)</sup>
<b>5. Organotin compounds</b>				
MBT(Monobutyltin)	1118-46-3	0,5 mg/kg (each)	0,5 mg/kg (each)	ISO/TS 16179 Solvent extraction / Derivatisation: Ethanol GC-MS analysis  DIN EN ISO 22744-1 Solvent extraction / Derivatisation: Methanol/Ethanol GC-MS analysis
DBT(Dibutyltin)	1002-53-5			
TBT(Tributyltin)	56573-85-4			
TPhT(Triphenyltin)	892-20-6			
DOT(Dioctyltin)	94410-05-6			
MOT(Monooctyltin)	15231-44-4			
DPhT(Diphenyltin)	1011-95-6			
TeBT(Tetrabutyltin)	1461-25-2			
TCyT(TricyclohexylTin)	NA			
TPT(Tripropyltin)	NA			
xxxTeET(Tetraethyltin)	597-64-8			
TBTO	56-35-9			
DBTC	683-18-1			
TPT	668-34-8			
DBB	75113-37-0			

		ALDI RSL Limits		
Substance	CAS-no.	Product section / Limits - Textiles <sup>1)</sup>	Product section / Limits - Shoes <sup>1)</sup>	Test Method <sup>9)</sup>
<b>6. PFCs (Perfluorocarbon / Polyfluorinated Compounds)</b>				
Sum of PFOA & salts	335-67-1	0.025 mg/kg	0.025 mg/kg	CEN/TS 15968 Solvent extraction: Methanol LC-MS-MS analysis EN ISO 23702-1 (Leather)
8:2 FTOH	678-39-7	1 mg/kg	1 mg/kg	
8:2 FTA	27905-45-9			
8:2 FTS	39108-34-4			
Me-PFOA	376-27-2			
Et-PFOA	3108-24-5			
8:2 FTMA	1996-88-9			
PFNA	375-95-1			
PFBS	375-73-5 or 59933-66-3	0,025 mg/kg (each)	0,05 mg/kg (each)	
PFHxS	355-46-4			
PFHxA	307-24-4			
PFBA	375-22-4			
PFPeA	2706-90-3			
PFHpA	375-85-9			
PFDA	335-76-2			
PFUnA	2058-94-8			
PFDoA	307-55-1			
PFTTrA	72629-94-8			
PfteA	376-06-7			
PFHpS	375-92-8			
PFDS	335-77-3			
PF-3,7-DMOA	172155-07-6			
HPFHpA	1546-95-8			
4HPFUnA	34598-33-9			
1H, 1H, 2H, 2H-PFOS	27619-97-2			



		ALDI RSL Limits		
Substance	CAS-no.	Product section / Limits - Textiles <sup>1)</sup>	Product section / Limits - Shoes <sup>1)</sup>	Test Method <sup>9)</sup>
PFOS & salts	1763-23-1	< 1 µg/m <sup>2</sup> (sum)	< 1 µg/m <sup>2</sup> (sum)	EN ISO 23702 -1
POSF	307-35-7			
PFOSA	754-91-6			
N-Me-FOSA	31506-32-8			
N-Et-FOSA	4151-50-2			
N-Me-FOSE alcohol	24448-09-7			
N-Et-FOSE alcohol	1691-99-2			
4:2 FTOH	2043-47-2			
6:2 FTOH	647-42-7	0,25 mg/kg (each)	0,5 mg/kg (each)	EN ISO 23702 -1
10:2 FTOH	865-86-1			
6:2 FTA	17527-29-6			
10:2 FTA	17741-60-5			
<b>7. Chloro benzenes</b>				
Dichlorobenzenes	various	1 mg/kg (sum)	1 mg/kg (sum)	EN 17137 Solvent extraction: Dichloromethane GC-MS analysis
1,2-Dichlorobenzene	95-50-1			
1,3-Dichlorobenzene	541-73-1			
1,4-Dichlorobenzene	106-46-7			
Trichlorobenzenes	various			
1,2,3-Trichlorobenzene	87-61-6			
1,2,4-trichlorobenzene	120-82-1			
1,3,5-Trichlorobenzene	108-70-3			
Tetrachlorobenzene	various			
1,2,3,4-tetrachlorobenzene	634-66-2			
1,2,3,5-tetrachlorobenzene	634-90-2			
1,2,4,5-tetrachlorobenzene	95-94-3			
Pentachlorobenzene	608-93-5			
Hexachlorobenzene	118-74-1			

		ALDI RSL Limits		
Substance	CAS-no.	Product section / Limits - Textiles <sup>1)</sup>	Product section / Limits - Shoes <sup>1)</sup>	Test Method <sup>9)</sup>
<b>Chloro-Toluenes (solvents and biocides. Production dyes. Chemical Intermediates. Antifelting)</b>				
2-chlorotoluene	95-49-8	1 mg/kg (sum)	1 mg/kg (sum)	EN 17137 Solvent extraction: Dichloromethane GC-MS analysis
3-chlorotoluene	108-41-8			
4-chlorotoluene	106-43-4			
2,3-dichlorotoluene	32768-54-0			
2,4-dichlorotoluene	95-73-8			
2,5-dichlorotoluene	19398-61-9			
2,6-dichlorotoluene	118-69-4			
3,4-dichlorotoluene	95-75-0			
2,3,6-trichlorotoluene	2077-46-5			
2,4,5-trichlorotoluene	6639-30-1			
Benzotrichloride	98-07-7			
alfa, 2,4-trichlorotoluene	94-99-5			
alfa, 2,6-trichlorotoluene	2014-83-7			
alfa, 3,4-trichlorotoluene	102-47-6			
alpha, alpha, 2,6-tetrachlorotoluene	81-19-6			
alpha, alpha, alpha, 2,-tetrachlorotoluene	2136-89-2			
alpha, alpha, alpha, 4-tetrachlorotoluene	5216-25-1			
2,3,4,5,6-pentachlorotoluene	877-11-2			
benzyl chloride	100-44-7			
<b>8. Chlorinated solvents</b>				
Dichloromethane	75-09-2	1 mg/kg (each) / 5 mg/kg (sum)	1 mg/kg (each) / 5 mg/kg (sum)	GC-MS Headspace  Solvent extraction GC-MS analysis  Thermal desorption analysis GC-MS analysis
Chloroform	67-66-3			
Tetrachloromethane	56-23-5			
1,1,2-Trichloroethane	79-00-5			
1,1-Dichloroethane	75-34-3			
1,2-Dichloroethane	107-06-2			
Trichloroethylene	79-01-6			
Perchloroethylene	127-18-4			
1,1,1-trichloroethane	71-55-6			
1,1,1,2-Tetrachloroethane	630-20-6			
1,1,2,2-Tetrachloroethane	79-34-5			
Pentachloroethane	76-01-7			
1,1-Dichloroethylene	75-35-4			

		ALDI RSL Limits		
Substance	CAS-no.	Product section / Limits - Textiles <sup>1)</sup>	Product section / Limits - Shoes <sup>1)</sup>	Test Method <sup>9)</sup>
<b>Other VOCs<sup>4)</sup></b>				
Methyl-ethyl ketone	78-93-3	10 mg/kg	50 mg/kg	Solvent extraction: Acetone GC-MS analysis  Thermal desorption analysis GC-MS analysis
Ethylbenzene	100-41-4	10 mg/kg	50 mg/kg	
Xylene	1330-20-7	10 mg/kg	30 mg/kg	
Cyclohexanone	108-94-1	10 mg/kg	50 mg/kg	
2-ethoxyethylacetate	111-15-9	10 mg/kg	50 mg/kg	
1,2,3-trichloropropane	96-18-4	10 mg/kg	50 mg/kg	
Acetophenone	98-86-2	10 mg/kg	10 mg/kg	
Naphtalene	91-20-3	2 mg/kg	2 / 5 mg/kg <sup>5)</sup>	
2-phenyl-2-propanole	617-94-7	10 mg/kg	10 mg/kg	
Bis-(2-methoxyethyl) ether	111-96-6	10 mg/kg	500 mg/kg (leather only)	
Styrene	100-42-5	10 mg/kg	50 mg/kg	
Benzene	71-43-2	1 mg/kg	1 mg/kg	
Toluene	108-88-3	10 mg/kg	10 mg/kg	
1-methyl-2-pyrrolidone	872-50-4	500 mg/kg <sup>7)</sup>	500 mg/kg	DIN CEN ISO/TS 16189 Solvent extraction: Methanol GC-MS analysis
N,N-dimethylacetamide	127-19-5	500 mg/kg <sup>7)</sup>	500 mg/kg	
<b>N, N-Dimethylformamide</b>				
N,N-dimethylformamide	68-12-2	500 mg/kg <sup>7)</sup>	100 mg/kg	DIN CEN ISO TS 16189 Solvent extraction: Methanol GC-MS analysis

		ALDI RSL Limits		
Substance	CAS-no.	Product section / Limits - Textiles <sup>1)</sup>	Product section / Limits - Shoes <sup>1)</sup>	Test Method <sup>9)</sup>
<b>9. Chloro phenols</b>				
Pentachlorophenols (PCP)	87-86-5	PCP - 0,05 / 0,25 mg/kg <sup>2)</sup> TeCP - 0,05 / 0,25 mg/kg <sup>2)</sup> (sum) TriCP - 0,2 / 1 mg/kg <sup>2)</sup> (sum)	0,5 / 1 mg/kg <sup>2)</sup> (each)	DIN EN ISO 17070 (Leather) or DIN 50009 (Textile); Solvent extraction or KOH extraction / Derivatization; GC-MS analysis or LC-MS (without derivatization)
Tetrachlorophenols (TeCP)	25167-83-3			
2,3,4,5-Tetrachlorophenol	4901-51-3			
2,3,4,6-Tetrachlorophenol	58-90-2			
2,3,5,6-tetrachlorophenol	935-95-5			
Trichlorophenol (TriCP)	25167-82-2			
2,4,6-trichlorophenol	88-06-2			
2,3,4-trichlorophenol	15950-66-0			
2,3,5-trichlorophenol	933-78-8			
2,3,6-trichlorophenol	933-75-5			
2,4,5-trichlorophenol	95-95-4			
3,4,5-trichlorophenol	609-19-8			
Dichlorophenols (DiCP)	25167-81-1			
2,3-dichlorophenol	576-24-9			
2,4-dichlorophenol	120-83-2			
2,5-dichlorophenol	583-78-8			
3, 4-dichlorophenol	95-77-2			
3, 5-dichlorophenol	591-35-5			
Mono Chlorophenol	various			
<b>10. SCCP</b>				
SCCP C <sub>10-13</sub>	85535-84-8	50 mg/kg (sum)	100 mg/kg (sum)	DIN EN ISO 18219 Solvent Extraction: Hexan / Toluol GC-NCI-MS analysis

		ALDI RSL Limits		
Substance	CAS-no.	Product section / Limits - Textiles <sup>1)</sup>	Product section / Limits - Shoes <sup>1)</sup>	Test Method <sup>9)</sup>
<b>11. Heavy metals</b>				
Cadmium(Cd)	7440-43-9	0,1 mg/kg (soluble) or; 40 mg/kg (total) for plastics and coated materials	0,1 mg/kg (soluble) or; 40 mg/kg (total) for plastics and coated materials	DIN EN 16711-1 (textile), DIN EN ISO 17072-2 (Leather) Microwave digestion, ICP-MS analysis (total) DIN EN 16711-2 (textile), DIN EN ISO 17072-1 (Leather) Acid perspiration extraction ICP analysis (Extractable)
Lead(Pb)	7439-92-1	0,2 mg/kg (soluble) or; 75 mg/kg (total) for plastics and coated materials	0,2 mg/kg (soluble) or; 75 mg/kg (total) for plastics and coated materials	
Mercury(Hg)	7439-97-6	0,02 mg/kg (soluble)	0,02 mg/kg (soluble)	DIN EN 16711-2 (textile), DIN EN ISO 17072-1 (Leather) Acid perspiration extraction ICP analysis (Extractable)
Nickel(Ni)	7440-02-0	1 mg/kg (soluble)	1 mg/kg (soluble)	
Hexavalent Chromium(Cr-VI)	18540-29-9	not detectable (< 0,5 mg/kg) (soluble)	not detectable (1 mg/kg; < 3 mg/kg for leather) (soluble)	EN ISO 17075-1 and and EN ISO 17075- 2:2017 for confirmation in case the extract causes interference.

		ALDI RSL Limits		
Substance	CAS-no.	Product section / Limits - Textiles <sup>1)</sup>	Product section / Limits - Shoes <sup>1)</sup>	Test Method <sup>9)</sup>
Arsenic(As)	7440-38-2	0,2 mg/kg (soluble)	0,2 mg/kg (soluble)	DIN EN 16711-2 (textile), DIN EN ISO 17072-1 (Leather) Acid perspiration extraction ICP analysis (Extractable)
Chromium(Cr)	7440-47-3	1 mg/kg (soluble)	0,2 g/kg (soluble)	
Copper(Cu)	7440-50-8	25 / 50 mg/kg <sup>2)</sup> (soluble)	50 mg/kg (soluble)	
Zinc(Zn)	7440-66-6	750 mg/kg <sup>8)</sup> (soluble)	750 mg/kg <sup>8)</sup> (soluble)	
Manganese(Mn)	7439-96-5	90 mg/kg (soluble)	90 mg/kg (soluble)	
Antimony (Sb)	7440-36-0	30 mg/kg (soluble)	30 mg/kg (soluble)	
Cobalt (Co) (Extractable heavy-metals by artificial acidic sweat)	7440-48-4	1 mg/kg (soluble)	4 mg/kg (soluble)	

		ALDI RSL Limits		
Substance	CAS-no.	Product section / Limits - Textiles <sup>1)</sup>	Product section / Limits - Shoes <sup>1)</sup>	Test Method <sup>9)</sup>

**RSL****Restricted Substances List**

These detection/reporting limits and test methods will be revised - at least yearly - to ensure that always the best current technology and the lowest detection/reporting limits are applied.

- Footnote 1) Textile products with leather as a main component are tested according to the Product section / Limits - Shoes
- Footnote 2) Limits set within the defined ranges depend on the requirement of use which apply to individual substances in certain articles (e.g. baby products <36month); excluding metal parts
- Footnote 3) Intentional use prohibited for all main components / 'confirmation of non-use'
- Footnote 4) Smell test based on SNV 195 651 to be carried out first. Further analytical testing only if significant deviations occur
- Footnote 5) 2 mg/kg for products with skin contact (AfPS)
- Footnote 6) Exception for products which must be treated hot (in wet or dry stage) during further processing: maximal 3.0%
- Footnote 7) For materials made of polyacrylonitrile (PAN), elastane (EL), polyurethane (PU), and aramides: 1000 mg/kg
- Footnote 8) It is intended to reduce the threshold limit to 90 ppm
- Footnote 9) Testing institutes always need to apply the latest test methods available for the defined standards and norms